



# Linyi Fanghua Steel Trading Co.,Ltd +8615376074407

Strap size				Average Strenth*		Yield		Coil Winding	Coil Weight		Strap Finish
Width		Thickness							lbs	kg	
inch	mm	inch	mm	lbs	N	ft/lb	m/kg		lbs	kg	
3/8	9.5	0.015	0.38	730	3 250	54.2	35.2	Mill	105	47.6	Curved Edge Painted & Waxed
3/8	9.5	0.020	0.51	900	4 000	39.3	26.4	Mill	105	47.6	Painted & Waxed
3/8	9.5	0.020	0.51	900	4 000	39.3	26.4	Mill	105	47.6	Curved Edge Painted & Waxed
1/2	12.7	0.020	0.51	1,170	5 200	29.4	19.8	Mill	105	47.6	Painted & Waxed
1/2	12.7	0.023	0.58	1,300	5 780	25.6	17.2	Mill	105	47.6	Painted & Waxed
5/8	15.9	0.020	0.51	1,460	6 490	23.6	15.9	Mill	105	47.6	Painted & Waxed
5/8	15.9	0.023	0.58	1,670	7 430	20.5	13.8	Mill	105	47.6	Painted & Waxed
3/4	19.0	0.020	0.51	1,750	7 780	19.6	13.2	Mill	105	47.6	Curved Edge Painted & Waxed
3/4	19.0	0.023	0.58	1,950	8 670	17.1	11.5	Mill	105	47.6	Painted & Waxed
1	25.4	0.020	0.51	1,540	6 850	29.4	19.7	Mill	105	47.6	Painted & Waxed
1	25.4	0.020**	0.51	1,920	8 540	23.6	15.8	Mill	105	47.6	Painted & Waxed
1	25.4	0.023	0.58	2,200	9 790	20.5	13.7	Mill	105	47.6	Painted & Waxed
1-1/4	31.75	0.025	0.64	4,800	21 350	9.4	6.3	Ribbon	110	49.9	Painted & Waxed
1-1/4	31.75	0.029	0.74	5,600	24 910	8.1	5.5	Ribbon	110	49.9	Painted & Waxed
1-1/4	31.75	0.029	0.74	5,600	34 910	8.1	5.5	Ribbon	110	49.9	Zinc
1-1/4	31.75	0.035	1.12	6,660	29 630	6.7	2.0	Ribbon	110	49.9	Painted & Waxed
1-1/4	31.75	0.044	1.12	8,450	37 590	5.3	3.5	Ribbon	110	49.9	Painted & Waxed
2	50.8	0.044	1.12	13,200	58 720	3.3	2.2	Ribbon	120	54.4	Painted & Waxed

Website <https://www.fanghuasteel.com>

Email: [Sales610@fanghuasteel.com](mailto:Sales610@fanghuasteel.com)

Linyi city, Shandong, China